

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions and listings of claims in the application.

LISTING OF CLAIMS

1. (Currently Amended) A wear-resistant aluminum alloy excelling in caulking properties, comprising 0.1 to 0.39 wt% of Mg, 3.0 to 6.0 wt% of Si, 0.01 to ~~[[0.50]]~~ 0.20 wt% of Cu, 0.01 to 0.5 wt% of Fe, 0.01 to 0.15 wt% of Mn, 0.01 to 0.5 wt% of Cr, less than 0.02 wt% of Zn, and the remainder being Al and unavoidable impurities; wherein a critical upsetting ratio of the alloy is greater than or equal to 43%; and wherein $0.79 \cdot (\text{wt\% of Mn}) + 0.26 \cdot (\text{wt\% of Mg}) \leq 0.22$.

2. (Currently Amended) A wear-resistant aluminum extruded product excelling in caulking properties, comprising 0.1 to ~~[[0.37]]~~ 0.39 wt% of Mg, 3.0 to 6.0 wt% of Si, 0.01 to ~~[[0.50]]~~ 0.20 wt% of Cu, 0.01 to 0.5 wt% of Fe, 0.01 to 0.15 wt% of Mn, 0.01 to 0.5 wt% of Cr, less than 0.02 wt% of Zn, and the remainder being Al and unavoidable impurities;

wherein a critical upsetting ratio of the extruded product is greater than or equal to 43%; and

wherein $0.79 \cdot (\text{wt\% of Mn}) + 0.26 \cdot (\text{wt\% of Mg}) \leq 0.22$.

3. – 4. (Cancelled)